

**Amendments to the Specification:**

Please replace paragraph [0030] with the following rewritten paragraph:

[0030] The binder, and the resulting toner particles made therefrom, of the invention are preferably made to have the following molecular weight values, each as determined by gel permeation chromatography (GPC) as known in the art and expressed in terms of polystyrene equivalent (pse).

Please replace paragraph [0031] with the following rewritten paragraph:

[0031] The binder used in the forming of the toner particles preferably has a weight average molecular weight of from about 20 to about 30 kilo polystyrene equivalent (kpse).